

an EnPro Industries company



Garlock Graph-Lock® 3124/3126

MATERIAL PROPERTIES

Composition: Graphite with a wire insert -Laminated layers of purified natural graphite flake that have been acid washed, expanded under heat, and then compressed into sheets with a minimum graphite content of 98%. This sheet contains a 0.0075" thick 316 stainless steel wire mesh (24 mesh) insert, bonded with a proprietary adhesive. This adhesive comprises less than 1% of the total laminated weight. Color: Black Temperature², °F (°C) Minimum: -400 (-240) Continuous Max³: +850 (+454) Pressure², Maximum, psiq (bar): 2000 (138) P x T (max.)², psig x °F (bar x °C) 1/16": 700,000 (25,000) 1/8": 350,000 (12,000) **Meets Specification:** Fire Safe

PHYSICAL PROPERTIES*

ASTM F36	Compressibility, %:	35
ASTM F36	Recovery, %:	20
ASTM F38	Creep Relaxation, %:	20
ASTM F152	Tensile, Across Grain, psi (N/mm ²):	2300 (15.8)
DIN 52913	Stability Under Stress, % (N/mm ²):	90
ASTM F1315	Density, lbs./ft.3 (grams/cm3):	70 (1.12)
ASTM F586	Design Factors	<u>1/16"</u>
	"m" factor:	2.0 2.0
	"y" factor, psi (N/mm²):	2500 (17.2) 2500 (17.2)
ASTM F104	Line Call Out:	F527000B4M4

SEALING CHARACTERISTICS

	ASTM F37B Fuel A	ASTM F37B Nitrogen	DIN 3535- 4 Gas Permeability
Gasket Load, psi (N/mm2):	500 (3.5)	3000 (20.7)	4640 (32)
Internal Pressure, psig (bar):	9.8 (0.7)	30 (2)	580 (40)
Leakage	1.0 ml/hr.	1.5 ml/hr.	0.4 cc/min

Chemical Impurity Data

Chemical Limits							
Leachable Levels, Max., ppm		Total Chemical Limits, M	ax., ppm				
Chlorides:	30	Total Sulfur:	1000				
Fluorides	30						

Notes:

This is a general guide and should not be the sole means of selecting or rejecting this material. ASTM test results in accordance with ASTM F-104; properties based on 1/32" (0.8mm) sheet thickness unless otherwise mentioned.

^{*} Values do not constitute specification Limits

² Based on ANSI RF flanges at our preferred torque. When approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum PxT, consult Garlock Applications Engineering.

³ Maximum temperature of +1000°F (+540°C) for GRAPH-LOCK HT.