Technical Data Sheet



novatec® PREMIUM II

engineered graphite with Kevlar®

Material profile:

- Highly compressed gasket material with good stress relaxation, temperature resistance and with good ductility
- The main components are graphite and aramid fibres, bound with NBR
- State-of-the-art material which combines the advantages of graphite and aramid.

Typical applications:

- For the general and chemical industry
- Oils and fats, acids and alkalis, solvents, refrigerants, water, steam

Supply data:

• Sheet sizes in mm: 2000x1500

• Thickness in mm: _ 1,0 / 1,5 / 2,0 / 3,0

- · Special sheet sizes upon request
- Other thicknesses upon request

General	Binders:	NBR		
data	Approvals:	DVGW / KTW / WRAS / W270 / VP401 / GL / BAM (max. 110 ℃ / 130 bar) / TA Luft / SVGW royal blue honeycomb with Frenzelit		
	Colour:			
	Branding:			
	Anti-stick coating: both sides A310 standard			
	Tolerances in thickness:	acc. DIN 28091-1		
	Property	Standard	Unity	Value *
Physical properties	Identification	DIN 28 091-2		FA - A 1 - O
(Gasket thickn. 2.00mm)	Density	DIN 28 090-2	[g/cm³]	1,70
	Tensile strength	DIN 52 910		
	longitudinal		[N/mm²]	18
	transverse		[N/mm²]	14
	Residual stress o _{dE/16}	DIN 52 913		
	175℃		[N/mm²]	l 37
	300℃		[N/mm²]	30
		ACTANT CO.	<u> </u>	
	Compressibility Recovery	ASTM F 36 J ASTM F 36 J	[%] [%]	7 60
	ritecovery	ASTNIT 300	[/o]	
	Cold compressibility ε _{KSW}	DIN 28 090-2	[%]	6
	Cold recovery ε _{KRW}	DIN 28 090-2	[%]	3
	Hotcreep ε _{WSW/200}	DIN 28 090-2	[%]	6
	Hot recovery ε _{WRW/200}	DIN 28 090-2	[%]	2
	Recovery R	DIN 28 090-2	[mm]	0,04
	Specific leakage rate	DIN 3535-6	[mg/(m₊s)]	≤ 0,1
	Specific leakage rate $\lambda_{2,0}$	DIN 28 090-2	[mg/(m-s)]	<u> </u>
			1	
	Fluid resistance	ASTM F 146		
	ASTM IRM903	5h/150 <i>°</i> C		
	Weight change		[%]	≤ 10
	Thickness increase		[%]	≤ 5
	ASTM Fuel B Weight change	5h/23℃	[%]	≤ 10
	Thickness increase		[%]	≤ 10 ≤5
	I III CKII GOO II I WI GADE		T v61	
	Chloride content	FZT PV-001-133	[ppm]	≤ 50

* = Mode (typical value) Issue: 06.10

Modifications: 9
Supersedes all prior versions

The technical data stated has been determined with standard material under laboratroy conditions. With the variety of installation and operating conditions no guarantee claim can be inferred regarding the behaviour of a flanged joint.

We reserve the right to product changes which serve the purpose of technical progress.